



SECTION 03360
CONCRETE FINISHES
CLASSIC TEXTURE

PART 1 GENERAL

1.1 SECTION INCLUDES

- A. Resurfacing of exterior concrete pavement.
- B. Resurfacing of interior concrete floors.
- C. Repair of vertical and overhead horizontal surfaces.
- D. Repair of damaged structural members.
- E. Elimination of water bearing cracks.

1.2 RELATED SECTIONS

- A Section 03300 - Cast-In-Place Concrete: New concrete.
- B Section 03330 - Architectural Concrete.
- C Section 02751 - Portland Cements Concrete Paving.
- D Section 03925 - Concrete Resurfacing and Rehabilitation.

1.3 REFERENCES

- A ANSI A118.4 - Specifications for Latex Portland Cement Mortar.
- B ASTM C67 - Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile.
- C ASTM A756 D & E – Standard Test Methods for Aging Test by Acceleration.
- D ASTM C1028 – Standard Test Methods for Coefficient of Friction.
- E ASTM D1242 – Standard Test Methods for Abrasion Resistance.
- F ASTM D570 – Standard Test Methods for Water Absorption.
- G ASTM D229 – Standard Test Methods for Chemical Resistance by 12 Reagents.

1.4 SUBMITALS

- A Submit under provisions of Section 01300.
- B Product Data: Manufacturer's data sheets on each product to be used, including:
 - 1. Preparation instructions and recommendations.
 - 2. Storage and handling requirements and recommendations.
 - 3. Installation methods.
- C Shop Drawings.
- D Selection Samples: For each finish product specified, two complete sets of color chips representing manufacturer's full range of available colors and patterns.
- E Verification Samples: For each finish product specified, two samples, minimum size 6 inches (150 mm) square, represent actual product, color, and patterns.

1.5 QUALITY ASSURANCE

- A Manufacturer Qualifications.
- B Installer Qualifications.
- C Mock-Up: Provide a mock-up for evaluation of surface preparation techniques and application workmanship.
 - 1. Finish areas designated by Architect.
 - 2. Do not proceed with remaining work until workmanship, color, and sheen are approved by Architect.
 - 3. Refinish mock-up area as required to produce acceptable work.

1.6 DELIVERY, STORAGE, AND HANDLING

- A. Properly label and identify all containers as Sundeck materials.
- B. Deliver and store all materials to prevent damage to product and containers.
- C. Store all material in a clean, dry location where temperatures are maintained between 40 and 90 degrees Fahrenheit.
- D. Comply with manufacture's Material Safety Data Sheets (MSDS) for delivery, storage and handling of products.

1.7 PROJECT CONDITIONS

- A Maintain environmental conditions (temperature, humidity, and ventilation) within limits recommended by manufacturer for optimum results. Do not install products under environmental conditions outside manufacturer's absolute limits.
- B Exterior Surfaces: Do not apply materials in wet weather.

PART 2 – PRODUCTS

2.1 MANUFACTURER

- A Acceptable Manufacturer: SUNDECK Products Inc, U.S.A., which is located at: 805 Ave H Suite 508; Arlington TX, 76011; ASD. Toll Free Tel: 877-478-6335; Email: request_info@sundek.com; Web: www.sundek.com;

2.2 CLASSIC TEXTURE SYSTEM

- A Copolymer Modified Cementitious Spray Texture Finish: Sundek Classic Texture as manufactured by Sundek Design Products.

2.3 ACCEPTABLE MATERIALS

- A Sundek Premix:
 - 1. Copolymer modified thin set cement coating to be used in conjunction with Sundek Additive, available in Tan, Grey, Red and White colors.
- B Sundek Primer/Additive:
 - 1. Vinyl acetate emulsion with 53% solids content.
- C Sundek Finish Coat:
 - 1. Water base acrylic color effect available in 16 standard colors or any customer color choice as special order.
- D Sundek Clear Finish Coat:
 - 1. Water based Acrylic Clear coat with 20% solids.
- E No materials can be substituted other than those specified by Sundeck Products, Inc.

2.4 PERFORMANCE

- A Weighs lbs./ft @ (3/16").....1.3 lbs.
- B Thickness (Typical).....3/16".
- C Bond Strength (ASTM C297).....469 psi.
- D Accelerated Aging (ASTM A756 D&E).....Unaffected.
- E Freeze-Thaw (ASTM C67).....No Breakage <1% weight loss.
- F Slip Resistance (S.C.O.F., ASTM C1028).....81 Wet-1.03 dry.
- G Abrasion (ASTM D1242).....0328 in. = 3000 psi Concrete.
- H Absorption (ASTM D570).....12.7%.
- I Percolation (ASTM D1242) 48"/48hr.....<1%.
- J Chemical Resistance (ASTM D229) 12 Reagents.....Unaffected.
- K Impact Resistance (Mil D3134 F).....No Breakage / < .62 in.
- L Concentrated Load Test (500 lb).....No Breakage / < .001 in.

PART 3 – EXECUTION

3.1 EXAMINATION

- A Concrete shall be structural sound, with required reinforcements and footings. Place and finish concrete in a skilled and workmanlike manner.
- B Install control joints throughout concrete as required to prevent cracking. All control joints must be honored and cannot be bridged with the Sundeek Classic Texture Effect installation.
- C Provide surface drainage at all points no less than 1/4 inch per linearfoot. Drainage correction is not guaranteed in the Sundeek Classic Texture Effect installation.

3.2 PREPARATION

- A. Clean concrete surface with high-pressure power washer.
- B. Remove dirt, grease, oil, curing compounds or other foreign substances, which may prevent proper bonding.
- C. Provide protective masking at all adjacent areas not to be coated.
- D. Repair cracks, surface damage and any corrective measures on concrete.

3.3 APPLICATION

- A. Spray or roll Sundeek Primer/Additive on area to be coated. Allow to dry and become transparent.
- B. SUNDEK BASE COAT (Required for blending repairs and profiling rough concrete surfaces).
 - 1. Apply Sundeek Base Coat using squeegee or trowel uniformly on area to be coated to a minimum thickness of 1/16" and allow drying.
 - 2. OPTIONAL MASONRY EFFECT - Place Sundeek Masonry Effects templates at area to be coated.
- C. Mix Sundeek Premix for Base Coat Application using mechanical agitation for 3-6 minutes as per mix design:
 - 1. Sundeek Additive/Primer.....0.5.gal.....4.5 lbs
 - 2. Sundeek Premix.....1 bag.....45 lbs
 - 3. *Clean Water.....1 gal
 - 4. *Water ratio will vary with temperature and humidity.
- D. Mix Sundeek Premix for Classic Texture using mechanical agitation for 3-6 minutes as per mix design:
 - 1. Sundeek Additive/Primer0.3 gal.....4.5 lbs
 - 2. Sundeek Premix.....1 Bag..... 45 lbs
 - 3. *Clean Water.....0.6 gal
 - 4. *Water ratio will vary with temperature and humidity.
- E. Spray Sundeek Classic Texture Premix thru hopper gun with air pressure at 12lbs.
- F. Knock down sprayed texture after it loses its gloss.
- G. Spray Sundeek Finish Coat to surface once is completely dry by roller or airless type sprayer and allow drying completely.
- H. OPTIONAL MASONRY EFFECTS - Remove Sundeek Masonry Effects templates when Colored

area is dry.

- I. OPTIONAL SCORING EFFECTS - Score desired pattern into Sundek Classic Texture Effect using masonry cutting wheel and grinder.
- J. Apply Sundek Clear Finish Coat with roller or sprayer.
- K. Remove all protective masking upon drying of Sundek Clear Finish Coat.

3.4 PROTECTION

- A. Protect all phases of Sundek Classic Texture Effect from moisture, freezing and foot traffic for 24 hours. Prevent vehicular traffic for 72 hours from finish of application.
- B. Owner or General Contractor will provide protection for finished Sundek Classic Texture Effect from damage by others until acceptance by responsible party.

3.5 MAINTENANCE

- A. Power wash or rinse thoroughly on a regular basis as needed.
- B. A mild solution of muriatic acid can be use for tougher stains.
- C. Touch up and perform all minor repairs as needed with touch up kits provided by Sundek during installation.
- D. Re-coloring of coating can be done to refresh the appearance and promote longevity.
- E. Contact your Sundek dealer for further assistance.

END OF SECTION