



Sundek Floor Wax

PRODUCT DESCRIPTION AND USE

Is a high gloss, non-yellowing acrylic floor polish for use on all types of sealed floors. It not only has a high gloss finish, it also can be a maintenance sacrificial coating. Maintenance can be done by spray and buff application. contains no toxic heavy metals or butyl solvents and has very low VOC's

Chemical Composition

Acrylic polymer emulsion, ethylene copolymers, proprietary additives and quality control agents.

Colors : Clear

Limitations

- Do not apply on exterior on-grade flagstone, sandstone or slate.
- Use on heavy traffic areas requires regular maintenance coating.
- Concrete must be absolutely dry.
- Do not apply when temperature is below 45°.

TECHNICAL DATA

Physical Properties

Type: Super acrylic floor polish

Color: Colorless, non-yellowing

Odor: Very mild

Toxicity: Non-toxic

Flammability: Non-Flammable

pH: 8.5–8.9

Dry time/re-coat (at 77° 2 mil wet film) 25 to 30 min

2 hr light traffic

72 hrs full cure

Higher temperatures will shorten dry times and lower temperature will lengthen it. Thicker films will take longer to dry

GENERAL INFORMATION

Surface Preparation

Surface must be clean, sound and absolutely dry. Surface preparation should be done with a floor machine and nylogrit type brush for smooth surfaces. If a cleaning solution is used, do not let solution dry on the surface. Rinse well with water and allow to dry overnight before coating.

T
E
C
H

•

A
P
P

•

S
P
E
C

Application Recommendations

Remove old polish thoroughly by scrubbing with SunKleen. Rinse floor well and let dry completely. Spread Sundek Floor Wax in a thin even coat over the floor using a Lambs wool Applicator or a clean yarn mop. Allow to dry completely, about 25 to 30 minutes. Apply a second coat and let dry completely before allowing traffic on the floor. Spray Buffing: Dilute 1 part of Sundek Floor Wax with 3 parts of water. Using a Trig Mist sprayer, mist lightly over a 1 sq. meter (10 sq. ft.) area and buff with a polishing pad until all liquid disappears and a brilliant shine appears. Repeat this until the entire floor is renovated and polished Maintenance: Occasional damp mopping with a neutral detergent will maintain the smooth glossy surface. In Heavy Traffic areas, after mopping and rinsing, let dry and apply a thin coat of Sundek Floor Wax.

Handling Precautions

Use adequate ventilation while installing.

Slip and Fall Precautions

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Sundek Products USA, Inc recommends the use of angular slip resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Sundek Products USA, Inc or its sales agents will not be responsible for injury incurred in a slip and fall accident.

WARRANTY INFORMATION

Sundeck Products Inc guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. SUNDECK PRODUCTS INC MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Sundeck Products Inc shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Sundeck Products Inc shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.